WORLD INTELLECTUAL PROPERTY ORGANIZATION



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification 6;	ı	(11) International Publication Number:	WO 98/00626
E21B 43/10, 29/10, 17/00, C21D 7/12, B21D 39/20	AI	(43) International Publication Date:	8 January 1998 (08.01.98)

(21) International Application Number: PCT/EP97/03489

(22) International Filing Date: 30 June 1997 (30.06.97)

(30) Priority Data:
96201809.9 1 July 1996 (01.07.96) EP
(34) Countries for which the regional or
international application was filed: GB et al.

(71) Applicant (for all designated States except CA): SHELL INTERNATIONALE RESEARCH MAATSCHAPPU B.V. [NL/NL]; Maatschappij B.V., Carel van Bylandtlaan 30, NL-2596 HR The Hague (NL).

(71) Applicant (for CA only): SHELL CANADA LTD. [CA/CA]: 400 - 4th Avenue, S.W., Calgary, Alberta T2P 2H5 (CA).

(72) Inventors: DONNELLY, Martin; Badhuisweg 3, NL-1031 CM Amsterdam (NL). FAURE, Alban, Michel; Volmerlaan 6, NL-2288 GD Rijswijk (NL). MARKETZ, Franz; Volmerlaan 6, NL-2288 GD Rijswijk (NL). STEWART, Robert, Bruce; Volmerlaan 6, NL-2288 GD Rijswijk (NL). LO-HBECK, Wilhelmus, Christianus, Maria; Volmerlaan 6, NL-2288 GD Rijswijk (NL). (81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BO, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, HU, IL, IS, IP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, UZ, VN, YU, ZW, ARIPO patent (GH, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM, European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG).


Published

With international search report.

(54) TIDE: METHOD FOR EXPANDING A STEEL TUBING AND WELL WITH SUCH A TUBING

(57) Abstract

A tubing (4) made of a formable steel grade which is subject to strain hardening without incurring any necking or ductile fracturing as a result of the expansion process is expanded by moving an expansion mandrel (5) having a non-metallic tapering outer surface through the tubing, thereby increasing the strength of the tubing while expansion forces remains low.



FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albatis	Z	Spain	LS	Lesotro	91
AM	Armenia	FL	Finland	LT	Lithereda	SK
AT	America	72.	France	w	Lunembourg	221
AU	Australia	GA	Gebon	LV	Letvia	82
AZ,	Azerbeijen	GB	United Kingdom	MC	Monaco	10
BA	Bossia and Heracgovina	CE	Georgia	MD	Republic of Moldova	TG
23	Barbados	CH	Chan	MG	Medagescar	TJ
38	Beiglam	CN	Quinca	MK	The former Yugoslav	Ď
37	Burkins Pero	GR	Greece		Republic of Macedoois	178
BG	Bulgaria	HU	Hungary	ML.	Mali	π
BJ	Denin	12	Ireland	MN	Mongolis	UA
BR	Beazil	IL.	Ternel	MR	Mauritania	UG
BY	Belares	15	locined	MW	Malawi	US
CA	Canada	IT	Italy	MX	Mexico	UZ
CF	Central African Republic	JP	Japan	NE	Niger	VN
CG	Compo	KE	Konya	NL	Netherlands	YU
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	zw
a	Cos Choire	KP	Democratic People's	NZ	New Zealand	211
CM	Cameroon		Republic of Kores	n	Poland	
CN	China	KR	Republic of Korea	ñ	Portugui	
CV	Cuba	KZ	Karakstan	RO	Romenia	
CZ	Czech Republic	ic	Saint Lucia	RU	Russian Federation	
DB	Germany	ũ	Liccincaucia	SD	Sadan	
DK	Denmark	LK	Sri Lanka	SE.	Sweden	
EE	Estosia	ia.	Liberia	SG.		
	-	1.41		36	Singapore	

:1

10

15

20

25

METHOD FOR EXPANDING A STEEL TUBING AND WELL WITH SUCH A TUBING

The invention relates to expansion of tubings. More particularly the invention relates to a method of expanding a steel tubing by moving an expansion mandrel through the tubing.

Numerous methods and devices are known for expansion of tubings.

European patent specification 643794 discloses a method of expanding a casing against the wall of an underground borehole wherein the casing is made of a malleable material which preferably is capable of plastic deformation of at least 25% unaxial strain and the casing may be expanded by an expansion mandrel which is pumped, pulled or pushed through the casing.

Other expansion methods and devices are disclosed in German patent specification No. 1583992 and in US patent specification Nos. 3,203,483; 3,162,245; 3,167,122; 3,326,293; 3,785,193; 3,489,220; 5,014,779; 5,031,699; 5,083,608 and 5,366,012.

Many of the known expansion methods employ an initially corrugated tube and the latter prior art reference employs a slotted tube which is expanded downhole by an expansion mandrel.

The use of corrugated or slotted pipes in the known methods serves to reduce the expansion forces that need to be exerted to the tube to create the desired expansion.

It is an object of the present invention to provide a method for expanding an at least partly solid, i.e. unslotted, tubing which requires exertion of a low force

WO 98/00626 PCT/EP97/03489

5

10

15

20

25

30

4

- 2 -

to expand the tubing and which provides a tubing having a larger diameter and higher strength than the unexpanded tubing and which can be carried out with a tubing which already may have a tubular shape before expansion.

The method according to the invention thereto comprises the step of moving an expansion mandrel through the tubing thereby plastically expanding the tubing, wherein an at least partly solid tubing is expanded which is made of a formable steel grade which is subject to strain hardening without incurring any necking and ductile fracturing as a result of the expansion process and an expansion mandrel is used which has along at least part of its length a tapering non-metallic surface.

As a result of strain hardening the tubing becomes stronger during the expansion process since for any further increment of expansion always a higher stress is required than for the preceding expansion.

It has been found that the use of a formable steel grade for the tubing in combination with a non-metallic tapering surface of the expansion mandrel has a synergetic effect since the resulting expanded tubing will have an adequately increased strength while the expansion forces remain low. The low yield strength and high ductility of the tubing before expansion enables, if the tubing is to be used in an underground borehole, the use of a tubing which is reeled from a reeling drum into the borehole.

It is observed that in the art of metallurgy the terms strain-hardening and work-hardening are synonyms and are both used to denote an increase of strength caused by plastic deformation.

The term formable steel grade as used in this specification means that the tubing is able to maintain

WO 98/00626 PCT/EP97/03489

5

10

15

20

25

30

- 3 -

its structural integrity while being plastically deformed into various shapes.

Ways of determining forming characteristics of a steel are set out in the Metals Handbook, 9th edition, volume 14, Forming and Forging, issued by ASM International, Metals Park, Ohio (USA).

The term necking refers to a geometrical effect leading to non-uniform plastic deformations at some - location by occurrence of a local constriction. From the point of necking on, the continual work hardening in the necked region no longer compensates for the continual reduction of the smallest cross-section in the neck, and therefore, the load carrying capacity of the steel decreases. With continuing loading, practically all further plastic deformation is restricted to the region of the neck, so that a highly non-uniform deformation occurs to develop in the necked region until fracture occurs.

The term ductile fracturing means that a failure occurs if plastic deformation of a component that exhibits ductile behaviour is carried to the extreme so that the component separates locally into two pieces. Nucleation, growth and coalescence of internal voids propagate to failure, leaving a dull fibrous rupture surface. A detailed description of the terms necking and ductile fracturing is given in the handbook "Failure of Materials in Mechanical Design" by J.A. Collins second edition, issued by John Wiley and Sons, New York (USA) in 1993.

Preferably the tubing is made of a high-strength steel grade with formability and having a yield strength-tensile strength ratio which is lower than 0.8 and a yield strength of at least 275 MPa. When used in this

10

15

20

specification, the term high-strength steel denotes a steel with a yield strength of at least 275 MPa.

It is also preferred that the tubing is made of a formable steel grade having a yield stress/tensile stress ratio which is between 0.6 and 0.7.

Dual phase (DP) high-strength, low-alloy (HSLA) steels lack a definite yield point which eliminates Luders band formation during the tubular expansion process which ensures good surface finish of the expanded tubular.

Suitable HSLA dual phase (DP) steels for use in the method according to the invention are grades DP55 and DP60 developed by Sollac having a tensile strength of at least 550 Mpa and grades SAFH 540 D and SAFH 590 D developed by Nippon Steel Corporation having a tensile strength of at least 540 MPa.

Other suitable steels are the following formable high-strength steel grades

- an ASTM A106 high-strength low alloy (HSLA) seamless pipe;
- an ASTM A312 austenitic stainless steel pipe, grade
 TP 304 L;
- an ASTM A312 austenitic stainless steel pipe, grade
 TP 316 L; and
- a high-retained austenite high-strength hot-rolled steel (low-alloy TRIP steel) such as grades SAFH 590 E, SAFH 690 E and SAFH 780 E developed by Nippon Steel Corporation.

The above-mentioned DP and other suitable steels each as a strain hardening exponent n of at least 0.16 which allows an expansion of the tubing such that the external diameter of the expanded tubing is at least 20% larger than the external diameter of the unexpanded tubing.

10

15

20

25

30

:1

Detailed explanations of the terms strain hardening, work hardening and the strain hardening exponent n are given in chapters 3 and 17 of the handbook "Metal Forming-Mechanics and Metallurgy", 2nd edition, issued by Prentice Hall, New Jersey (USA), 1993.

Suitably, the expansion mandrel contains an expansion section that has a conical ceramic outer surface. If the expansion mandrel is pumped through the tubing then the mandrel preferably comprises a sealing section which is located at such a distance from the tapering expansion section that when the expansion mandrel is moved through the tubing by means of exerting a hydraulic pressure behind the mandrel the sealing section engages a plastically expanded part of the tubing. This will generally be achieved if said distance is at least three times the wall thickness of the expanded tubing.

The use of a ceramic conical surface reduces friction forces during the expansion process and by having a sealing section which engages the expanded tube it is avoided that hydraulic forces would result in an excessive expansion of the tubing.

In such case it is preferred that the expansion mandrel contains a vent line for venting to the surface any fluids that are present in the borehole and tubing ahead of the expansion mandrel.

Alternatively the tubing is expanded such that the outer diameter of the expanded tubing is slightly smaller than the internal diameter of the borehole or of any casing that is present in the borehole and any fluids that are present in the borehole and tubing ahead of the expansion mandrel are vented to surface via the annular space that remains open around the tubing after the expansion process.

10

15

20

25

30

The invention also relates to a well provided with a tubing which is expanded using the method according to the invention. In such case the tubing may serve as production tubing through which hydrocarbon fluid is transported to the surface and a reelable service and/or kill line passes through at least a substantial part of the length of the tubing, through which line fluid can be pumped towards the bottom of the borehole while hydrocarbon fluid is produced via the surrounding production tubing. The use of such an expanded production tubing allows the use of almost the full wellbore for the transport of hydrocarbon fluids so that a relatively slim borehole may be utilized to attain the desired production rate.

Alternatively the tubing may be expanded against the inner surface of a casing which is present in the borehole. In such case the tubing may either be used as a production tubing and/or as a protective cladding for protecting the well casing against corrosive well fluids and damage from tools that may be lowered into the well during maintenance and workover operations.

These and other objects, features and advantages of the method and well system according to the present invention will be apparent from the accompanying claims, abstract and the following detailed description with reference to the accompanying drawing, in which Fig. 1 is schematic longitudinal sectional view of an underground borehole in which a tubing is expanded in accordance with the method according to the invention.

Now referring to Fig. 1, there is shown a borehole traversing an underground formation 1 and a casing 2 that is fixed within the borehole by means of an annular body of cement 3.

WO 98/00626 PCT/EP97/03489

5

10

15

20

25

30

A production tubing 4 which is made of a dual phase, high-strength low-alloy (HSLA) steel or other formable high-strength steel is suspended within the casing 2.

- 7 -

An expansion mandrel 5 is moved in longitudinal direction through the tubing 4 thereby expanding the tubing 4 such that the outer diameter of the expanded tubing is slightly smaller than or is about equal to the internal diameter of the casing 2.

The expansion mandrel 5 is equipped with a series of ceramic surfaces 6 which restrict frictional forces between the pig and tubing 4 during the expansion process. In the example shown the semi top angle A of the conical ceramic surface that actually expands the tubing is about 25°. It has been found that zirconium oxide is a suitable ceramic material which can be formed as a smooth conical ring. Experiments and simulations have shown that if the semi cone top angle A is between 20° and 30° the pipe deforms such that it obtains an S-shape and touches the tapering part of the ceramic surface 6 essentially at the outer tip or rim of said conical part and optionally also about halfway the conical part.

The experiments also showed that it is beneficial that the expanding tubing 4 obtains an S-shape since this reduces the length of the contact surface between the tapering part of the ceramic surface 6 and the tubing 4 and thereby also reduces the amount of friction between the expansion mandrel 5 and the tubing 4.

Experiments have also shown that if said semi top angle A is smaller than 15° this results in relatively high frictional forces between the tube and pig, whereas is said top angle is larger than 30° this will involve redundant plastic work due to plastic bending of the tubing 4 which also leads to higher heat dissipation and

10

15

20

25

30

to disruptions of the forward movement of the pig 5 through the tubing 4. Hence said semi top angle A is preferably selected between 15° and 30° and should always be between 5° and 45°.

Experiments have also shown that the tapering part of the expansion mandrel 5 should have a non-metallic outer surface to avoid galling of the tubing during the expansion process. The use of a ceramic surface for the tapering part of the expansion mandrel furthermore caused the average roughness of the inner surface of the tubing 4 to decrease as a result of the expansion process. The experiments have also shown that the expansion mandrel 5 provided with a ceramic tapering surface 6 could expand a tubing 5 made of a formable steel such that the outer tubing diameter D2 after expansion was at least 20% larger than the outer diameter D1 of the unexpended tubing and that suitable formable steels are dual phase (DP) high-strength low alloy (HSLA) steels known as DP55 and DP60; ASTM Al06 HSLA seamless pipe, ASTM A312 austenitic stainless steel pipes, grades TP 304 L and TP 316 L and a high-retained austenite highstrength hot rolled steel, known as TRIP steel manufactured by the Nippon Steel Corporation.

The mandrel 5 is provided with a pair of sealing rings 7 which are located at such a distance from the conical ceramic surface 6 that the rings 7 face the plastically expanded section of the tubing 4. The sealing rings serve to avoid that fluid at high hydraulic pressure would be present between the conical ceramic surface 6 of the mandrel 5 and the expanding tubing 4 which might lead to an irregularly large expansion of the tubing 4.

10

15

20

25

30

The expansion mandrel 5 is provided with a central vent passage 7 which is in communication with a coiled vent line 8 through which fluid may be vented to the surface. After completion of the expansion process the pig 5 may be pulled up to surface by the vent line and a coiled kill and/or service line (not shown) may be lowered into the expanded tubing 4 to facilitate injection of kill and/or treatment fluids towards the hydrocarbon fluid inflow zone which is normally be done via the annulus between the production tubing and the well casing. However, if the tubing 4 is expanded to a smaller diameter then the residual annular space between the casing 2 and expanded tubing 4 can be used for venting of fluids during the expansion process and for injection of fluids during the production process, in which case there is no need for using a vent line 8 and kill and/or service lines.

In conventional wells it is often necessary to use a production tubing having an outer diameter which is less than 50% of the inner diameter of the well casing to enable a smooth insertion of the tubing even if the well is deviated and the casing has an irregular inner surface. Therefore it is apparent that the in-situ tubing expansion method according to the present invention enhances an efficient use of the wellbore.

It will be understood that instead of moving the expansion mandrel through the tubing by means of hydraulic pressure, the mandrel can also be pulled through the tubing by means of a cable or pushed through the tubing by means of pipe string or rod.

The method according to the invention can also be used to expand tubings that are used outside a wellbore, for example to expand oilfield tubulars at surface

15

à.

facilities or to expand a tubing inside an existing tubing which has been damaged or corroded.

The invention will now be further described on the basis of the following comparative experiments.

5 Experiment 1

An expansion mandrel having a conical ceramic surface (semi top angle A of cone = 20°) was moved through a conventional oil field tubular, known as casing grade L80 13% Cr, which is a widely used casing type, having an initial outer diameter of 101.6 mm (4"), an initial wall thickness of 5.75 mm, a burst pressure of 850 bar and a strain hardening exponent n = 0.075. The expansion mandrel was designed such that the outer diameter of the expanded tubular would be 127 mm, so that the increase in diameter would be 20%. The tubular burst during the expansion process. Analysis showed that the ductility limit of the material had been exceeded so that ductile fracturing occurred.

Experiment 2

20 An experiment was carried out with a coiled tubing of the type QT-800 which is increasingly used as a production tubing in oil or gas wells. The tubing had an initial outer diameter of 60.3 mm, a wall thickness of 5.15 mm, a burst pressure of 800 bar and a strain 25 hardening exponent n = 0.14. An expansion mandrel was moved through the tubing which mandrel comprised a conical ceramic surface such that the semi top angle A of a cone enveloping the conical surface was 5° and which was designed such that the outer diameter of the expanded tubing would be 73 mm (increase of about 21%). This 30 tubing burst during the expansion process. Analysis revealed that due to high friction forces the expansion

10

:1

pressure had exceeded the burst pressure of the pipe during the expansion process.

Experiment 3

An experiment was carried out with a seemless pipe made of a formable steel grade known as ASTM A 106 Grade B. The pipe had an initial outer diameter of 101.6 mm (4"), an initial wall thickness of 5.75 mm and a strain hardening exponent n=0.175.

An expansion mandrel was pumped through the pipe, which mandrel comprised a ceramic conical surface such that the semi top angle A of a cone enveloping the conical surface was 20° and such that the outer diameter of the expanded pipe was 127 mm (5") and the outer diameter increased by 21%.

The pipe was expanded successfully and the hydraulic pressure exerted to the mandrel to move the mandrel through the pipe was between 275 and 300 bar. The burst pressure of the expanded pipe was between 520 and 530 bar.

CLAIMS

- 1. A method of expanding a steel tubing, the method comprising the step of moving an expansion mandrel through the tubing thereby plastically expanding the tubing, wherein an at least partly solid tubing is expanded which is made of a formable steel grade which is subject to strain hardening without incurring any necking and ductile fracturing as a result of the expansion process and an expansion mandrel is used which has along at least part of its length a tapering non-metallic
- 10 surface.

5

- 2. The method of claim 1, wherein the tubing is made of a formable steel grade having a yield strength-tensile strength ratio which is lower than 0.8 and a yield strength of at least 275 MPa.
- 3. The method of claim 1 or 2, wherein the tubing is made of a steel having a yield strength-tensile strength ratio which is between 0.6 and 0.7.
 - 4. The method of claim 1, 2 or 3, wherein the tubing is made of a dual phase (DP) high-strength low alloy (HSLA)
- 20 steel.

25

L

- 5. The method of claim 4, wherein the tubing is made of Sollac grade DP55 or DP60 having a tensile strength of at least 550 Mpa or Nippon grade SAFH 540 D or SAFH 590 D.
- 6. The method of claim 1, 2 or 3 wherein the tubing is made of a formable high-strength steel grade which is selected from the following group of steel grades:
 - an ASTM Al06 high-strength low alloy (HSLA) seamless pipe;

25

- an ASTM A312 austenitic stainless steel pipe, grade
 TP 304 L;
- an ASTM A312 austenitic stainless steel pipe, grade
 TP 316 L; and
- 5 a high-retained austenite high-strength hot rolled steel which is known as TRIP steel.
 - 7. The method of any preceding claim, wherein the tubing is expanded such that the external diameter of the expanded tubing is at least 20% larger than the external diameter of the unexpanded tubing and wherein the strain hardening exponent n of the formable steel of the tubing is at least 0.16.
- 8. The method of any preceding claim, wherein the expansion mandrel comprises a tapering expansion section which has a smooth ceramic outer surface which is oriented at an acute angle A which is between 5° and 45° with respect to a longitudinal axis of the mandrel and which induces the tubing to expand without inducing any galling of the tubing and such that the average roughness of the inner surface of the tubing decreases as a result of the expansion process.
 - 9. The method of claim 8, wherein the ceramic outer surface of the tapering expansion section is made of zirconium oxide and is oriented at an acute angle A which is between 15° and 30° with respect to a longitudinal axis of the mandrel.
 - 11. The method of any preceding claim, wherein the tubing is expanded by pumping the expansion mandrel through the tubing.
- 12. The method of claim 7 and 11, wherein the expansion mandrel comprises a sealing section which is located at such a distance from the expansion section that when the expansion mandrel is pumped through the tubing the

WO 98/00626 PCT/EP97/03489

5

10

15

a.


expansion process.

- 14 -

sealing section engages a plastically expanded part of the tubing.

- 13. The method of claim 11 or 12, wherein the tubing is expanded inside an underground borehole and the expansion mandrel contains a vent line for venting any fluids that are present in the tubing ahead of the expansion mandrel to the surface.
- 14. The method of claim 11 or 12, wherein the tubing is expanded inside an underground borehole such that the outer diameter of the expanded tubing is slightly smaller than the internal diameter of the borehole or of any casing that is present in the borehole and any fluids that are present in the borehole and tubing ahead of the expansion mandrel are vented to surface via the annular space that remains open around the tubing after the
 - 15. The method of any preceding claim, wherein the tubing is lowered into an underground borehole after reeling the tubing from a reeling drum.
- 20 16. A well provided with a tubing which is expanded using the method of any preceding claim, wherein the tubing serves as a production tubing through which hydrocarbon fluid is transported to the surface and a reelable service and/or kill line passes through at least a substantial part of the length of the interior of the tubing, through which line fluid can be pumped towards the bottom of the borehole while hydrocarbon fluid is
- 17. A well provided with a tubing which is expanded using
 the method according to any one of claims 1-13, wherein
 the tubing is expanded against the inner surface of a
 casing which is present in the borehole.

produced via the surrounding production tubing.



iŁ.

Inten and Application No PCT/EP 97/03489

4 01 400	CONTROL OF OUR PROPERTY.		
ÎPC 6	IFICATION OF SUBJECT MATTER E21843/10 E21829/10 E218	B17/00 C2107/12	B21039/20
According t	o International Patent Classification (IPC) or to both national of	lessification and IDC	
	SEARCHED		
Minimum di IPC 6	coumentation searched (classification system followed by class E21B C21D B21C B21D	anfication symbols) ,	
	Jion ee arched other than minimum documentation to the exten		
Electronio d	tals base consulted during the international search (name of d	ata base and, where practical, ecerch t	erms vood)
C. DOCUM	ENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of t	the relevant passages	Relevant to staim No.
A	US 4 533 405 A (SPONSELLER) 6 see column 1, line 15 - line see column 2, line 67 - column see column 4, line 26 - line see column 14, line 47 - line see column 17, line 25 - line	27 an 3, line 2 29 5 51	1
A	CH 180 467 A (THEINTZ) 16 Jan see page 1, right-hand column line 19	nuary 1936 a, line 17 -	1
A	US 4 938 266 A (TOMITA) 3 Jul see the whole document	-/	1
X Furt	ner documents are finted in the continuation of box C.	X Patent family member	a are fluted in annex.
"A" decume consider "E" earlier of Sing d "L" docume which electron other of docume other of learning inter the state of t	nd which may throw doubte on priority elean(e) or is also to establish the publication data of another is or other special reason (as specified) and referring to an oral disclosum, use, exhibition or means. In published prior to the international filing data but and the priority data eleaned.	or priority date and not in eliable to sectoralised the pri- invention. "X" determined of perfector relevance occurrence	of or earnout be someideed to when the document is then alone renne; the chairmed invention white an invention step when the the one or more other such docu- poing obvious to a person skilled some patent family
	edual completion of the international search 8 September 1997	Oats of mailing of the intern 08.10.97	lational search report
Name and n	naling address of the ISA. European Petent Office, P.B. 5618 Petenteen 2 NL - 2280 HV Rijestje Tel. (+31-70) 340-2040, Tr. 31 651 epo nl, Fax: (+31-70) 340-3016	Authorized officer Sagna, H	

Forte PCT/ISA/218 (second sheet) (July 1982)

Inter. and Application No PCT/EP 97/03489

	Non) DOCUMENTS CONSIDERED TO BE RELEVANT	
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 93 25799 A (SHELL CANADA LIMITED) 23 December 1993 cited in the application see abstract see page 2, line 32 - line 35 see claim 10 see page 4, line 20 - line 26 see page 5, line 23 - line 35 see page 3, line 17 - line 20	1
A	US 3 901 063 A (NILESHWAR) 26 August 1975 see column 1, line 34 - line 40	1
A	DE 93 04 218 U (PURMO AG) 8 July 1993 see page 4, line 14 - line 16	1
A	US 5 366 012 A (LOHBECK) 22 November 1994 cited in the application see column 2, line 48 - column 3, line 5 see column 3, line 34 - line 57	1
A	DE 15 83 992 B (MANNESMANN A.G.) 9 June 1971 cited in the application see claim 1	1
A	GB 861 603 A (LA SALLE STEEL COMPANY) 22 February 1961 see page 1, line 11 - line 15 see claim 1	1
A	US 5 352 406 A (BARTERI) 4 October 1994 see column 1, line 14 - line 21 see column 1, line 68 - column 2, line 2 see column 2, line 64 - line 68	1
A	US 4 832 757 A (COX) 23 May 1989 see abstract see column 1, line 13 - line 14 see column 1, line 45 - line 51 see column 2, line 34 - line 45	1
A	PATENT ABSTRACTS OF JAPAN vol. 007, no. 281 (C-200), 15 December 1983 & JP 58 157948 A (KAWASAKI SEITETSU KK), 20 September 1983, see abstract	1
	-/	

Form PCT/SA/Z10 (continuation of excord sheet) (July 1962)

Ł

Inter. nal Application No PCT/EP 97/03489

* viogeta	Alon) OCCIMENTS CONSIDERED TO BE RELEVANT Clation of document, with indication, where appropriate, of the relevant passages	Retovert to claim No.
	DATABASE WPI Section Ch, Week 8343 Derwent Publications Ltd., London, GB; Class M24, AN 83-798811 XP002020522 & JP 58 157 948 A (KAWASAKI STEEL), 20 September 1983 see abstract	. 1
	PATENT ABSTRACTS OF JAPAN vol. 015, no. 064 (C-0806), 15 February 1991 & JP 02 290920 A (NIPPON STEEL CORP), 30 November 1990, see abstract	1
4	OATABASE WPI Section Ch, Week 9103 Derwent Publications Ltd., London, GB; Class H01, AN 91-018662 XP002020523 & JP 02 290 920 A (NIPPON STEEL CORP) , 30 November 1990 see abstract	1
١	US 5 224 560 A (FERNANDEZ) 6 July 1993 see column 10, line 61 - column 11, line 3	1
4	US 4 960 643 A (LEMELSON) 2 October 1990 see abstract	1
A	GB 2 155 950 A (NIPPON STEEL CORPORATION) 2 October 1985 see abstract	1
A	US 5 014 779 A (MELING) 14 May 1991 cited in the application see column 4, line 12 - line 28	1
A	US 3 489 220 A (KINLEY) 13 January 1970 cited in the application see claim 1	1
A	US 3 162 245 A (HOWARD) 22 December 1964 cited in the application see column 2, line 69 - column 3, line 10	1
A	US 3 203 483 A (VINCENT) 31 August 1965 cited in the application see column 3, line 36 - line 65	1

information on patent family members

Intel and Application No PCT/EP 97/03489

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US 4533405 A	06-08-85	US 4453986 A	12-06-84
CH 180467 A		NONE	
**************************************		RUNE	
US 4938266 A	93-97-99	JP 1156421 A	20-06-89
		JP 2017505 C	19-02-96
		JP 1156422 A	20-06-89
		JP 2017506 C	19-02-96
		DE 3874100 A	01-10-92
		EP 0320003 A	14-06-89
WO 9325799 A	23-12-93	AU 670948 B	08-08-96
		AU 4324493 A	04-81-94
		CA 2137560 A	23-12-93
		DE 69306110 D	02-01-97
		DE 69306110 T	05-06-97
		EP 0643794 A	22-03-95
		JP 7507610 T	24-08-95
		NO 944721 A	07-12-94
		NZ 253124 A	27-02-96
		US 5348095 A	20-09-94
US 3901063 A	26-08-75	NONE	••••••••••
DE 9304218 U	68-67-93	NONE	
US 5366012 A	22-11-94	AU 672008 B	19-09-96
		AU 4324593 A	04-01-94
		CA 2137565 A	23-12-93
		DE 69305852 D	12-12-96
		DE 69305852 T	22-05-97
		WO 9325800 A	23-12-93
		EP 0643795 A	22-03-95
		JP 7507611 T	24-08-95
		MD 960219 A	31-05-97
		NO 944746 A	03-02-95
		NZ 253125 A	27 -0 2-96
DE 1583992 B	09-06-71	NONE	

Information on palent family mambers

PCT/EP 97/03489

Patent document cited in search report	Publication data	Palent family member(s)	Publication date
GB 861603 A		NONE	
US 5352406 A	04-10-94	IT 1263251 B EP 0594935 A NO 931530 A	05-08-96 04-05-94 28-04-94
US 4832757 A	23-05-89	NONE	•••••••••••••••••••••••••••••••••••••••
US 5224560 A	06-07-93	US 5137097 A AU 9042291 A CN 1061457 A WO 9208033 A US 5199516 A	11-08-92 26-05-92 27-05-92 14-05-92 06-04-93
US 4960643 A	02-19-9 0	US 5456406 A US 4974498 A US 5096352 A US 5040501 A US 5067826 A US 5255929 A US 5132587 A US 5288556 A US 5284394 A US 5332348 A US 5360227 A	10-10-95 04-12-90 17-03-92 20-08-91 26-11-91 26-10-93 21-07-92 22-02-94 08-02-94 26-07-94 01-11-94
GB 2155950 A	02-10-85	JP 60187663 A JP 60187664 A CA 1239568 A DE 3507124 A FR 2560608 A	25-09-85 25-09-85 26-07-88 12-09-85 06-09-85
US 5014779 A	14- 05 -91	CA 1322151 A W0 9005831 A AU 621350 B AU 3189889 A DE 3887905 D EP 0397875 A NO 174637 B	14-09-93 31-05-90 12-03-92 12-06-90 24-03-94 22-11-90 28-02-94

Æ

Information on patent family members

PCT/EP 97/03489

Patent document ted in search report	Publication date	Patent femily	Publication
		member(s)	date
S 3489220 A	13-01-70	NONE	
S 3162245 A	22-12-64	NONE	
S 3203483 A	31-08-65	NONE	
		,	
-		-	
-			
	•	•	

This Page is Inserted by IFW Indexing and Scanning Operations and is not part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

BLACK BORDERS

IMAGE CUT OFF AT TOP, BOTTOM OR SIDES

FADED TEXT OR DRAWING

BLURRED OR ILLEGIBLE TEXT OR DRAWING

SKEWED/SLANTED IMAGES

COLOR OR BLACK AND WHITE PHOTOGRAPHS

GRAY SCALE DOCUMENTS

LINES OR MARKS ON ORIGINAL DOCUMENT

REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY

IMAGES ARE BEST AVAILABLE COPY.

OTHER:

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.